

Iranian Journal of Physics Research, Vol. 21, No. 2, 2021 DOI: 10.47176/ijpr.21.2.61073

## Study of the effect of temperature on optical and topographical properties of RF Magnetron Sputtered ZrO<sub>2</sub> thin films

R Shakouri<sup>1</sup>, E Nahvifard<sup>1</sup>, S Miri<sup>2</sup>, and N Talebani<sup>1</sup>

Department of Physics, Faculty of science, Imam Khomeini International University, Qazvin, Iran
Iranian National Center for Laser Science and Technology, Tehran, Iran

E-mail: shakouri@sci.ikiu.ac.ir

(Received 09 June 2020; in final form 23 January 2021)

## **Abstract**

In this paper,  $ZrO_2$  thin films were grown on glass substrates using RF magnetic sputtering method. In three separate experiments, three samples of  $ZrO_2$  film were prepared at various temperatures. Three temperatures of  $25\,^{\circ}$ C (laboratory temperature),  $150\,^{\circ}$ C and  $250\,^{\circ}$ C were selected for three samples, respectively. Except for temperature, other parameters such as pressure, film growth rate, substrate to target distance and deposition time were the same for all three samples. Optical properties and morphology of the samples were investigated. The morphology of the samples was determined by atomic force microscopy (AFM) images and the transmittance was measured using optical spectroscopy. The optical constants of the films were also calculated using their spectrum. The results show that the effect of temperature is especially evident on the optical properties of the films. As the temperature increases from the ambient temperature to  $250\,^{\circ}$ C, the refractive index changes from n=2.11 to n=2.18. Moreover, increasing the temperature, causes the absorption of the layer to increase. The morphology of the films also changes slightly by changing temperature. The average roughness of all three samples is less than half a nanometer..

Keywords: thin film ZrO<sub>2</sub>, sputtering, morphology film, optical properties

For full article, refer to the Persian section